

BINDAKOTE

THE FOLLOWING DATA REFERS TO BINDAKOTE COVER BILUCIDO 2/side coated

	Method		+/-	250 g/m ²	300 g/m ²	350 g/m ²
Basis weight	ISO 536	g/m ²	5%	250	300	350
Caliper	ISO 534	µm	5%	255	315	365
Bulk	ISO 534	cm ³ /g	-	1,0	1,0	1,0
Gloss 20°	ISO 2813	%	>	45	45	45
ISO Brightness	ISO 2470	%	2	83	83	83
CIE Whiteness	ISO 11475	%	7	90	90	90
Moisture Content	ISO 287	%	1	5,5	5,5	5,5
L&W Stiffness MD (15°/50mm)	ISO 2493	mN	>	120	220	350
L&W Stiffness CD (15°/50mm)	ISO 2493	mN	>	60	110	175

THE FOLLOWING DATA REFERS TO BINDAKOTE ICE WHITE

	Method		+/-	250 g/m ²	250 g/m ² BILUCIDO	300 g/m ²	350 g/m ²
Basis weight	ISO 536	g/m ²	5%	250	250	300	350
Caliper	ISO 534	µm	5%	315	255	387	450
Bulk	ISO 534	cm ³ /g	-	1,3	1	1,3	1,3
Gloss 20°	ISO 2813	%	>	45	45	45	45
ISO Brightness	ISO 2470	%	2	84	84	84	84
CIE Whiteness	ISO 11475	%	7	111	111	111	111
Moisture Content	ISO 287	%	1	5,5	5,5	5,5	5,5
L&W Stiffness MD (15°/50mm)	ISO 2493	mN	>	140	120	240	400
L&W Stiffness CD (15°/50mm)	ISO 2493	mN	>	70	60	120	200

THE FOLLOWING DATA REFERS TO BINDAKOTE ICE WHITE LABEL

	Method		+/-	80 g/m ²
Basis weight	ISO 536	g/m ²	5%	80
Caliper	ISO 534	µm	5%	92
Bulk	ISO 534	cm ³ /g	-	1,1
Gloss 20°	ISO 2813	%	>	25
ISO Brightness	ISO 2470	%	2	84
CIE Whiteness	ISO 11475	%	7	111
WET Tensile Strength MD	ISO 3781	KN/m	>	0,9
Cobb 120"	ISO 535	g/m ²	2	22
Moisture Content	ISO 287	%	1	5,5
L&W Stiffness MD (15°/10mm)	ISO 2493	mN	>	100
L&W Stiffness CD (15°/10mm)	ISO 2493	mN	>	50

THE FOLLOWING DATA REFERS TO BINDAKOTE FOLDING BOARD

	Method		+/-	300 g/m ²	325 g/m ²	400 g/m ²	480 g/m ²
Basis weight	ISO 536	g/m ²	5%	300	325	400	480
Caliper	ISO 534	µm	5%	387	429	450	550
Bulk	ISO 534	cm ³ /g	-	1,3	1,3	1,1	1,1
Gloss 20°	ISO 2813	%	>	45	45	45	45
ISO Brightness	ISO 2470	%	2	80	80	80	80
CIE Whiteness	ISO 11475	%	7	80	80	80	80
Moisture Content	ISO 287	%	1	5,5	5,5	5,5	5,5
L&W Stiffness MD (15°/50mm)	ISO 2493	mN	>	240	320	500	750
L&W Stiffness CD (15°/50mm)	ISO 2493	mN	>	120	160	250	375