

arto[®] magic

Bilderdruckpapier, holzfrei, weiß,
glänzende Oberfläche

Technische Daten

arto[®] magic

Flächengewicht	ISO 536	g/qm	90	100	115	130	150
Spezifisches Volumen	ISO 534	cm ³ /g	0,74	0,74	0,74	0,74	0,74
Weißer D65	ISO 2470-2	%	98	98	98	98	98
CIE-Weißer	ISO 11475	%	125	125	125	125	125
Opazität	ISO 2471	%	91	92	94,5	95	97
Glanz Hunter	ISO 8254-1	%	70	70	70	70	70
Glanz Lehmann	ISO 8254-2	%	70	70	70	70	70
Glätte PPS 10	ISO 8791-4	µm	0,7	0,7	0,7	0,7	0,7

arto[®] magic

Flächengewicht	ISO 536	g/qm	170	200	250	300	350
Spezifisches Volumen	ISO 534	cm ³ /g	0,74	0,74	0,74	0,75	0,78
Weißer D65	ISO 2470-2	%	98	98	98	98	98
CIE-Weißer	ISO 11475	%	125	125	125	125	125
Opazität	ISO 2471	%	97,5	98,5	99,5	99,6	99,8
Glanz Hunter	ISO 8254-1	%	72	75	75	75	75
Glanz Lehmann	ISO 8254-2	%	72	75	75	75	75
Glätte PPS 10	ISO 8791-4	µm	0,7	0,7	0,7	0,7	0,7

Alle Angaben sind Richtwerte des Herstellers, die industriellen üblichen Schwankungen unterliegen können.

Einsatzbereiche

Werbematerial, Geschäftsberichte, Bücher, Broschüre, Kataloge, Direktmailing, Zeitschriftencover, Zeitschriften, Zeitungsbeilagen

Drucktechnologie

- Bogenoffset

Technische Hinweise

- EU Umweltzeichen
- EN 71/3:1988 D Sicherheit von Spielzeug
- 94/62 EG Schwermetallzertifikat
- BfR-Lebensmittelzertifikat
- Alterungsbeständigkeit (DIN EN ISO 9706)

Umweltrelevante Produktzertifikate und Informationen

- FSC® Mix Credit (FSC® C003945)
- PEFC-zertifiziert (PEFC/13-32-045)

Hersteller-Zertifikate

- Qualitätsmanagementsystem (ISO 9001)
- Umweltmanagementsystem (ISO 14001)
- Energiemanagement (ISO 50001)
- Arbeitssicherheits- und Gesundheitsmanagement (ISO 45001)
- Eco-Management and Audit Scheme (EMAS)

Zertifikate



Manufactured
in a mill with
quality
management



Manufactured
in a mill with
environmental
management



Manufactured
in a mill with
energy
management



Manufactured
in a mill with
health and safety
management



Manufactured
in an EMAS
certified mill



Permanent
Paper