

arto[®] silk

Bilderdruckpapier, holzfrei, weiß, mit seidenmatter Oberfläche
und schöner Haptik

Technische Daten

arto[®] silk

Flächengewicht	ISO 536	g/qm	90	100	115	135	150
Dicke	ISO 534	µm	80	86	100	115	131
Spezifisches Volumen	ISO 534	cm ³ /g	0,89	0,86	0,87	0,85	0,87
CIE-Weiße D65/10°	ISO 11475	%	121,3	121,3	121,3	121,3	121,3
Opazität	ISO 2471	%	92	93	95	96	97
Rauhigkeit Parker	ISO 8791-4	µm ≤ 1,30*Std	1,9	1,9	1,9	1,7	1,7
Feuchte	TAPPI T502	% ±7	50	50	50	50	50

arto[®] silk

Flächengewicht	ISO 536	g/qm	170	200	250	300	350
Dicke	ISO 534	µm	152	181	239	299	358
Spezifisches Volumen	ISO 534	cm ³ /g	0,89	0,91	0,96	1	1,02
CIE-Weiße D65/10°	ISO 11475	%	121,3	121,3	121,3	121,3	121,3
Opazität	ISO 2471	%	97,5	-	-	-	-
Rauhigkeit Parker	ISO 8791-4	µm ≤ 1,30*Std	1,7	1,7	1,7	1,9	2,1
Feuchte	TAPPI T502	% ±7	50	50	50	50	50

Alle Angaben sind Richtwerte des Herstellers, die industrieüblichen Schwankungen unterliegen können.

Distributor:

OVOL Papier Deutschland GmbH
Osterbekstraße 90a
22083 Hamburg
Deutschland
www.ovol.de

Bitte beachten Sie, dass diese Aussagen Richtwerte sind. Gültig ab 03/25

Einsatzbereiche

Bücher, Broschüren, Kataloge, Umschläge,
personalisierte Direktmails, Prospekte, Einlagen,
Verpackungen, Postkarten

Drucktechnologie

- Flexo-, Offset- und Tiefdruck
- Laser und Trockentoner

Umweltrelevante Produktzertifikate und Informationen

- FSC® Mix Credit (FSC® C003945)
- PEFC-zertifiziert (PEFC/13-32-045)
- EFC-zertifiziert

Hersteller-Zertifikate

- Qualitätsmanagementsystem (ISO 9001)
- Umweltmanagementsystem (ISO 14001)
- Energiemanagement (ISO 50001)
- Arbeitssicherheits- und Gesundheitsmanagement (ISO 45001)
- Eco-Management and Audit Scheme (EMAS)



Das Zeichen für
verantwortungsvolle
Waldwirtschaft



PEFC/13-32-045



Manufactured in
a mill with quality
management



Manufactured in
a mill with
environmental
management



Manufactured in
a mill with
energy management



Manufactured in
a mill with health
and safety
management



Manufactured in
an EMAS
certified mill